



AAROPRENE® CFPP 2000 SERIES REINFORCED COMPOUNDS

AAROPRENE® CFPP

PROPERTIES		ASTM METHOD	UNITS OF MEASURE	2010	2020	2030	2040
GENERAL	CALCIUM CONTENT	D-2584	%	10	20	30	40
	MOLD SHRINKAGE	D-955	in/in	.012	.010	.009	.008
	SPECIFIC GRAVITY	D-792	g/cm ³	.97	1.04	1.14	1.24
MECHANICAL	TENSILE STRENGTH @ 73°F	D-638	psi	4650	4200	3800	3700
	FLEXURAL MODULUS	D-790	psi	270,000	290,000	310,000	330,000
	IZOD IMPACT @ 73° (NOTCHED)	D-256	ft-lbs/in	.55	.77	.82	1.01
THERMAL	MELT FLOW INDEX (230/2.16)	D-1238	g/10 min	8-12	8-12	8-12	8-12
	DEFLECTION TEMPERATURE	D-648	°F @ 66psi	200	210	220	235

Melt flow index may be specified.

Color may be specified.



The information and recommendations in this publication are, to the best of our knowledge, reliable. Suggestions concerning uses or applications are only the opinion of Aaron Ind. Corp. and users should perform their own tests to determine the suitability of these products for their own particular purposes. However, because of numerous factors affecting results, Aaron Ind. Corp. MAKES NO WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING THOSE OF MANUFACTURING AND FITNESS FOR PURPOSE, other than that the material conforms to the applicable current Standard Specifications Statements herein, therefore, should not be construed as representations or warranties. The responsibility of Aaron Ind. Corp. for claims arising out of breach of warranty, negligence, strict liability or otherwise is limited to the purchase price of the material. Statements concerning the use of the products of formulations described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is assumed.