


## AAROPRENE® GFN & G/MFN 6000 SERIES REINFORCED COMPOUNDS

### AAROPRENE®

PROPERTIES	ASTM METHOD	UNITS OF MEASURE	GFN		MFN	G/MFN	
			6013	6033	6001	6002	
<b>GENERAL</b>	GLASS CONTENT	D-2584	%	13	33	—	—
	MOLD SHRINKAGE	D-955	in/in	.005	.004	—	.01
	SPECIFIC GRAVITY	D-792	g/cm <sup>3</sup>	1.20	1.37	1.47	1.48
<b>MECHANICAL</b>	TENSILE STRENGTH @ 73°F	D-638	psi	16,500	23,500	12,000	17,000
	FLEXURAL MODULUS	D-790	psi	800,000	1,200,000	760,000	950,000
	IZOD IMPACT @ 73° (NOTCHED)	D-256	ft-lbs/in	1.1	2.1	2.0	.08
<b>THERMAL</b>	DEFLECTION TEMPERATURE	D-648	°F @ 66psi	—	—	—	420

Color may be specified.



The information and recommendations in this publication are, to the best of our knowledge, reliable. Suggestions concerning uses or applications are only the opinion of Aaron Ind. Corp. and users should perform their own tests to determine the suitability of these products for their own particular purposes. However, because of numerous factors affecting results, Aaron Ind. Corp. MAKES NO WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING THOSE OF MANUFACTURING AND FITNESS FOR PURPOSE, other than that the material conforms to the applicable current Standard Specifications Statements herein, therefore, should not be construed as representations or warranties. The responsibility of Aaron Ind. Corp. for claims arising out of breach of warranty, negligence, strict liability or otherwise is limited to the purchase price of the material. Statements concerning the use of the products of formulations described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is assumed.