



**POLYPROPYLENE  
COMPOUNDED RESINS**

**SPECIALTY RESINS AND COMPOUNDS**

**AAROLENE® ARPP 200 SERIES  
POLYPROPYLENE COMPOUNDED RESINS  
ARPP200-1 PP BLACK HOMOPOLYMER HIGH FLOW**

	PROPERTIES	ASTM METHOD	UNITS OF MEASURE	H 200-1
<b>GENERAL</b>	SPECIFIC GRAVITY	D-792	g/cm <sup>3</sup>	.900
	MOLD SHRINKAGE	D-955	in/in	.022
<b>MECHANICAL</b>	TENSILE STRENGTH @ Yield	D-638	PSI	5100
	FLEXURAL MODULUS	D-790	PSI	200,000
	IZOD IMPACT @ 73° (Notched)	D-256	ft-lbs./in.	0.6
<b>THERMAL</b>	MELT FLOW INDEX (230/2.16)	D-1238	g/10 min	30
	DEFLECTION TEMPERATURE	D-648	°F @ 66PSI	230

**FEATURES: AN PRE-COLORED BLACK HOMOPOLYMER POLYPROPYLENE RESIN SPECIFICALLY DESIGNED FOR ALL INJECTION MOLDING APPLICATIONS.**

The information and recommendations in this publication are, to the best of our knowledge, reliable. Suggestions concerning uses or applications are only the opinion of Aaron Ind. Corp. and users should perform their own tests to determine the suitability of these products for their own particular purposes. However, because of numerous factors affecting results, Aaron Ind. Corp. MAKES NO WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING THOSE OF MANUFACTURING AND FITNESS FOR PURPOSE, other than that the material conforms to the applicable current Standard Specifications Statements herein..