

SPECIALTY RESINS AND COMPOUNDS

AAROLENE®ARPS 100 SERIES Compounded Resins ARPS 100-3 HIPS BLACK EXTRUSION GRADE

	PROPERTIES	ASTM METHOD	UNITS OF MEASURE	HI 100-3
GENERAL	SPECIFIC GRAVITY	D-792	g/cm ³	1.05
	MOLD SHRINKAGE	D-955	in/in	.006
MECHANICAL	TENSILE STRENGTH@ YIELD	D-638	PSI	3300
	FLEXURAL MODULUS	D-790	PSI	300,000
	IZOD IMPACT @ 73° Notched	D-256	Ft.-lbs/in	2.3
THERMAL	MELT FLOW INDEX (200/5)	D-1238	g/10 min	4
	DEFLECTION TEMPERATURE	D-648	°f@ 66psi	172
<p>FEATURES: A High Impact polystyrene custom colored black featuring good flow and excellent toughness for all Extrusion Applications.</p>				

The information and recommendations in this publication are, to the best of our knowledge, reliable. Suggestions concerning uses or applications are only the opinion of Aaron Ind. Corp. and users should perform their own tests to determine the suitability of these products for their own particular purposes. However, because of numerous factors affecting results, Aaron Ind. Corp. MAKES NO WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING THOSE OF MANUFACTURING AND FITNESS FOR PURPOSE, other than that the material conforms to the applicable current Standard Specifications Statements herein, therefore, should not be construed as representations or warranties