



**ELASTOMERIC
COMPOUND**

SPECIALTY RESINS AND COMPOUNDS

**AAOPRENE® ATPR 1000 Series
ECATPR1050 NATURAL**

	PROPERTIES	ASTM METHOD	UNITS OF MEASURE	1050
GENERAL	SPECIFIC GRAVITY	D-792	g/cm ³	1.01
	MOLD SHRINKAGE	D-955	in/in	.006
MECHANICAL	TENSILE STRENGTH @ BREAK	D-638	psi	670
	TENSILE MODULUS	D-790	psi	270
	IZOD IMPACT @ 73° (notched)	D-256	ft-lbs/in	NB
THERMAL	MELT FLOW INDEX (200/5)	D-1238	g/10 min	8
	DEFLECTION TEMPERATURE	D-648	°F @ 264 psi	140

FEATURES: A SBS Based Thermoplastic rubber compound natural in color for all extrusion applications featuring good chemical resistance and toughness

The information and recommendations in this publication are, to the best of our knowledge, reliable. Suggestions concerning uses or applications are only the opinion of Aaron Ind. Corp. and users should perform their own tests to determine the suitability of these products for their own particular purposes. However, because of numerous factors affecting results, Aaron Ind. Corp. MAKES NO WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING THOSE OF MANUFACTURING AND FITNESS FOR PURPOSE, other than that the material conforms to the applicable current Standard Specifications Statements herein..