

SPECIALTY RESINS AND COMPOUNDS

AAROPRENE ® ATPR 2000 SERIES ECATPR2040 BLACK

	PROPERTIES	ASTM METHOD	UNITS OF MEASURE	2040
GENERAL	SPECIFIC GRAVITY	D-792	g/cm ³	1.03
	MASS BULK DENSITY	D-792	lbs/ft ³	35
	COLOR	Visual	Visual	Black
MECHANICAL	HARDNESS	D-2240	A shore	40
	TENSILE STRENGTH @ Break	D-412	psi	900
	TENSILE MODULUS	D-412	psi	180
	ELONGATION @ BREAK	D-412	%	800
	TABER ABRASION	D-1044	Mg Loss	290
	ELASTIC MODULUS	D-412	psi	400
THERMAL	MELT FLOW INDEX	D-1238	g/10 min	15
FEATURES: A black thermoplastic SEBS rubber compound specifically designed for the injection molding of industrial gaskets.				

The information and recommendations in this publication are, to the best of our knowledge, reliable. Suggestions concerning uses or applications are only the opinion of Aaron Ind. Corp. and users should perform their own tests to determine the suitability of these products for their own particular purposes. However, because of numerous factors affecting results, Aaron Ind. Corp. MAKES NO WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING THOSE OF MANUFACTURING AND FITNESS FOR PURPOSE, other than that the material conforms to the applicable current Standard Specifications Statements herein, therefore, should not be construed as representations or warranties