



**POLYPROPYLENE  
VIRGIN**

**SPECIALTY RESINS AND COMPOUNDS**

**VIRGIN AVPP 200 PP SERIES  
AVPP200-1 PP NATURAL HOMO 12 MELT**

	PROPERTIES	ASTM METHOD	UNITS OF MEASURE	HOMO 200-1
<b>GENERAL</b>	SPECIFIC GRAVITY	D-792	g/cm <sup>3</sup>	.900
	MOLD SHRINKAGE	D-955	in/in	.022
<b>MECHANICAL</b>	TENSILE STRENGTH @ Yield	D-638	PSI	5400
	FLEXURAL MODULUS	D-790	PSI	2.0x10
	IZOD IMPACT @ 73°F (Notched)	D-256	ft-lbs./in.	0.6
<b>THERMAL</b>	MELT FLOW INDEX	D-1238	g/10 min	12
	DEFLECTION TEMPERATURE	D-648	°F @ 66PSI	220°F
<b>FEATURES:</b> A Virgin polypropylene specifically designed for all injection molding applications				

The information and recommendations in this publication are, to the best of our knowledge, reliable. Suggestions concerning uses or applications are only the opinion of Aaron Ind. Corp. a tests to determine the suitability of these products for their own particular purposes. However, because of numerous factors affecting results, Aaron Ind. Corp. MAKES NO WARRANTY OR IMPLIED, INCLUDING THOSE OF MANUFACTURING AND FITNESS FOR PURPOSE, other than that the material conforms to the applicable current Standard Specifications Staten