



High Density Polyethylene (AVPE)

Processing HDPE Natural Virgin (20 Melt)

Convert Imperial		
Mold		20 – 60 Deg. C
Melt		180 – 250 Deg. C
Max Temp		280 Deg. C
Drying		80 Rarely
Injection Speed		Medium to High
Purge		HDPE

Physical Characteristics

Structure		Crystalline
Opacity		Translucent to Opaque
Physical		Tough, Waxy Surface
Specific Gravity		0.97
Shrinkage		1.0 to 2.0%
Melting Point		100 Deg. C
HDT		60 – 90 Deg. C
Service Temp		84 Deg. C

HDPE is generally easy to process, with higher molecular weight grades having stiffer flow properties.

Applications include: Containers, Storage, seals & closures.

The information and recommendations in this Processing Guideline are, to the best of our knowledge, reliable. Suggestions concerning uses or applications are only the opinion of Aaron Industries Corp. and users should perform their own tests to determine the suitability of these products for their own particular purposes. However, because of numerous factors affecting results, Aaron Industries Corp. MAKES NO WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING THOSE OF MANUFACTURING AND FITNESS FOR PURPOSE.