

Polypropylene (AVPP)

Processing PP Natural Virgin

	<u>Convert Imperial</u>	
Mold		10 – 60 Deg. C
Melt		180-240 Deg. C
Max Temp		300 Deg. C
Drying		70-90 Deg. C
Injection Speed		Medium to High
Purge		PP

Physical Characteristics

Structure		Semi Crystalline
Opacity		Clear to Opaque
Physical		Tough, Rigid
Specific Gravity		0.85-0.95
Shrinkage		1.2 to 1.7%
Melting Point		100 Deg. C
HDT		71 – 115 Deg. C
Service Temp		85 Deg.C

PP Offers excellent processing, good surface finish and food contact approval.

Applications include: automotive interior, exterior, household and medical applications.

The information and recommendations in this Processing Guideline are, to the best of our knowledge, reliable. Suggestions concerning uses or applications are only the opinion of Aaron Industries Corp. and users should perform their own tests to determine the suitability of these products for their own particular purposes. However, because of numerous factors affecting results, Aaron Industries Corp. MAKES NO WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING THOSE OF MANUFACTURING AND FITNESS FOR PURPOSE.