




**AAROLENE® ARPE 300 SERIES
COMPOUNDED RESINS**

**AAROLENE®
ARPE**

PROPERTIES		ASTM METHOD	UNITS OF MEASURE	LD 300-1	HD 300-2
GENERAL	SPECIFIC GRAVITY	D-792	g/cm ³	.920-.926	.950-.962
	MOLD SHRINKAGE	D-955	in/in	.015	.015
MECHANICAL	TENSILE STRENGTH @ 73°F	D-638	psi	2900	4100
	FLEXURAL MODULUS	D-790	psi	42,000	100,000
	IZOD IMPACT @ 73° (NOTCHED)	D-256	ft-lbs/in	No Break	No Break
THERMAL	MELT FLOW INDEX (190/2.16)	D-1238	g/10 min	2-50	.3-50
	DEFLECTION TEMPERATURE	D-648	°F @ 66psi	163	180

Specific gravity may be specified.
Melt flow index may be specified.

Color may be specified.



The information and recommendations in this publication are, to the best of our knowledge, reliable. Suggestions concerning uses or applications are only the opinion of Aaron Ind. Corp. and users should perform their own tests to determine the suitability of these products for their own particular purposes. However, because of numerous factors affecting results, Aaron Ind. Corp. MAKES NO WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING THOSE OF MANUFACTURING AND FITNESS FOR PURPOSE, other than that the material conforms to the applicable current Standard Specifications Statements herein, therefore, should not be construed as representations or warranties. The responsibility of Aaron Ind. Corp. for claims arising out of breach of warranty, negligence, strict liability or otherwise is limited to the purchase price of the material. Statements concerning the use of the products of formulations described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is assumed.