



AAROPRENE® ATPR 2000 SERIES ELASTOMERIC COMPOUNDS

AAROPRENE® ATPR

PROPERTIES		ASTM METHOD	UNITS OF MEASURE	2000 50A	2000 60A	2000 70A	2000 80A
GENERAL	SPECIFIC GRAVITY	D-792	g/cm ³	.95–1.15	.95–1.15	.95–1.10	.95–1.10
	HARDNESS ±3	D-2240	Shore A	50	60	70	80
MECHANICAL	TENSILE STRENGTH	D-412	psi	652	545	980	1600
	ELONGATION @ BREAK	D-412	%	800	600	700	600
	TENSILE MODULUS	D-412	psi	180	210	230	300
	TEAR STRENGTH	D-624	(PIW) Die C	110	135	155	335
THERMAL	MELT FLOW INDEX "G" (200/5)	D-1238	g/10min	12	13	8	20
	TABER ABRASION	D-1044	Mg Loss (H-18, 1KC)	290	260	125	110

Durometer values may be specified.

Color may be specified.



The information and recommendations in this publication are, to the best of our knowledge, reliable. Suggestions concerning uses or applications are only the opinion of Aaron Ind. Corp. and users should perform their own tests to determine the suitability of these products for their own particular purposes. However, because of numerous factors affecting results, Aaron Ind. Corp. MAKES NO WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING THOSE OF MANUFACTURING AND FITNESS FOR PURPOSE, other than that the material conforms to the applicable current Standard Specifications Statements herein, therefore, should not be construed as representations or warranties. The responsibility of Aaron Ind. Corp. for claims arising out of breach of warranty, negligence, strict liability or otherwise is limited to the purchase price of the material. Statements concerning the use of the products of formulations described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is assumed.