




AAROPRENE® GFABS 4000 SERIES REINFORCED COMPOUNDS

AAROPRENE® GFABS

PROPERTIES		ASTM METHOD	UNITS OF MEASURE	4010	4020	4030	4040
GENERAL	GLASS CONTENT	D-2584	%	10	20	30	40
	MOLD SHRINKAGE	D-955	in/in	.003	.002	.002	.002
	SPECIFIC GRAVITY	D-792	g/cm ³	1.10	1.22	1.28	1.32
MECHANICAL	TENSILE STRENGTH @ 73°F	D-638	psi	9400	11,000	13,500	14,700
	FLEXURAL MODULUS	D-790	psi	580,000	815,000	930,000	992,000
	IZOD IMPACT @ 73° (NOTCHED)	D-256	ft-lbs/in	1.4	1.2	1.0	.98
THERMAL	MELT FLOW INDEX	D-1238	g/10 min	5-10	5-10	5-10	5-10
	DEFLECTION TEMPERATURE	D-648	°F @ 66psi	210	220	225	230

Melt flow index may be specified.

Color may be specified.



The information and recommendations in this publication are, to the best of our knowledge, reliable. Suggestions concerning uses or applications are only the opinion of Aaron Ind. Corp. and users should perform their own tests to determine the suitability of these products for their own particular purposes. However, because of numerous factors affecting results, Aaron Ind. Corp. MAKES NO WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING THOSE OF MANUFACTURING AND FITNESS FOR PURPOSE, other than that the material conforms to the applicable current Standard Specifications Statements herein, therefore, should not be construed as representations or warranties. The responsibility of Aaron Ind. Corp. for claims arising out of breach of warranty, negligence, strict liability or otherwise is limited to the purchase price of the material. Statements concerning the use of the products of formulations described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is assumed.