



**VIRGIN AVPP 200
POLYPROPYLENES**

AVPP

PROPERTIES		ASTM METHOD	UNITS OF MEASURE	H 200-1	C 200-2
GENERAL	SPECIFIC GRAVITY	D-792	g/cm ³	.90	.90
	MOLD SHRINKAGE	D-955	in/in	.022	.022
MECHANICAL	TENSILE STRENGTH @ 73°F	D-638	psi	4500	5500
	FLEXURAL MODULUS	D-790	psi	200,000	250,000
	IZOD IMPACT @ 73° (NOTCHED)	D-256	ft-lbs/in	0.6	2
THERMAL	MELT FLOW INDEX (230/2.16)	D-1238	g/10 min	8-12	8-12
	DEFLECTION TEMPERATURE	D-648	°F @ 66psi	262	262

Melt flow index may be specified



The information and recommendations in this publication are, to the best of our knowledge, reliable. Suggestions concerning uses or applications are only the opinion of Aaron Ind. Corp. and users should perform their own tests to determine the suitability of these products for their own particular purposes. However, because of numerous factors affecting results, Aaron Ind. Corp. MAKES NO WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING THOSE OF MANUFACTURING AND FITNESS FOR PURPOSE, other than that the material conforms to the applicable current Standard Specifications Statements herein, therefore, should not be construed as representations or warranties. The responsibility of Aaron Ind. Corp. for claims arising out of breach of warranty, negligence, strict liability or otherwise is limited to the purchase price of the material. Statements concerning the use of the products of formulations described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is assumed.